Stabilization of a hydrophobic natural dye by intercalation into organo-montmorillonite

著者	Kohno Yoshiumi, Inagawa Mayu, Ikoma Shuji, Shibata Masashi, Matsushima Ryoka, Fukuhara Choji, Tomita Yasumasa, Maeda Yasuhisa, Kobayashi Kenkichiro
journal or publication title	Applied Clay Science
volume	54
number	3-4
page range	202-205
year	2011-12
出版者	Elsevier
権利	Copyright (C) 2011 Elsevier B.V. All rights reserved.
注記	NOTICE: this is the author's version of a work that was accepted for publication in Applied Clay Science. Changes resulting from the publishing process, such as peer review, editing, corrections, structural formatting, and other quality control mechanisms may not be reflected in this document. Changes may have been made to this work since it was submitted for publication. A definitive version was subsequently published in Applied Clay Science, VOL54, ISSUE3-4, 28 September 2011. DOI10.1016/j.clay.2011.09.001
URL	http://hdl.handle.net/10297/7626

doi: 10.1016/j.clay.2011.09.001

18

19 Abstract

20 The stability of the naturally occurring annatto dye against irradiation with visible light
21 was enhanced by intercalation into octyl trimethylammonium and dodecyl
22 trimethylammonium montmorillonite. The intercalated dye exhibited improved light fastness.
23 The effect of the stability enhancement was more distinct with dodecyl trimethylammonium
24 montmorillonite. The reason of the improvement was proved to be the hindrance from the
25 contact with the atmospheric oxygen because the dye molecules were incorporated in the
26 interlayer space. The amount of the adsorbed dye could be increased more than ten times
27 when an aqueous ethanolic solution was used instead of pure ethanol as solvent in the
28 adsorption process.

29

30

31 *Keywords: annatto dye, organo-montmorillonite, surfactant, light fastness, stabilization*

32

1. Introduction

Annatto dye is a natural organic pigment belonging to the carotenoids. It is widely used as a food colorant (C. I. Natural Orange 4) because of its low toxicity. The main components of the annatto dye are bixin and norbixin (Scheme 1). The annatto dye is less stable and easily discolored. Light is the most destructive agent (Najar et al., 1988). Therefore, efforts were made to conserve the color of the annatto dye (Prabhakara Rao et al., 2005). Protection of the dye molecule by other materials is one of the approaches. For example, annatto dye was stored in oleoresin to keep its color (Balaswamy et al., 2006) or incorporated in cyclodextrin to improve the stability against light or heat (Lyng et al., 2005).

---Scheme 1---

There are some reports concerning the stability enhancement of the dye by the incorporation into the interlayer space of clay minerals (Bauer et al., 2003; Bujdák et al., 2002; Chakraborty et al., 2011; Giustetto et al., 2011). We recently studied the stability enhancement of natural dyes by intercalating them into the interlayer space of several clay minerals. Anthocyanin, a cationic natural dye, was intercalated into montmorillonite (Kohno et al., 2009a). The color stability in alkaline medium or against visible light was drastically

improved by the intercalation. On the other hand, the anionic dye carmine was intercalated into hydrotalcite, and the light fastness of the dye was enhanced. However, the annatto dye could not be intercalated into the polar interlayer space of the hydrotalcite (Kohno et al., 2009b). Bixin and norbixin can be considered as anionic dyes because they have carboxyl group(s). However, the long conjugated double bond chain in their structure makes the annatto dye strongly hydrophobic. Therefore, to incorporate the annatto dye between the clay mineral layers, the interlayer space must be hydrophobized.

Organo-clay minerals were reported to have the ability to incorporate various organic compounds (Lagaly et al., 2006) such as dyes (Sasai et al., 2004; Sasai et al., 2003; Tong et al., 2010), pesticides (Cruz-Guzman et al., 2005; Groisman et al., 2004) or herbicides (Celis et al., 2007; Seki and Yurdakoç, 2005). We succeeded in the intercalation of non-ionic (hydrophobic) 2-hydroxychalcone derivatives into organo-montmorillonite and the photochemical conversion of the chalcone to the flavylum form (Kohno et al., 2011). In this study, we report the intercalation of the hydrophobic natural annatto dye into organo-montmorillonite to enhance its light stability.

2. Experimental

35

36 *2.1 Sample preparation*

37

38 The annatto dye (ANA) was supplied by Wako Chemical Co. and used without further
39 purification. Montmorillonite Kunipia F (denoted as KF) was supplied by Kunimine Industry.
40 The cation exchange capacity (CEC) of KF was 1.19 meq/g. Octyl trimethylammonium
41 bromide (OTAB) and dodecyl trimethylammonium bromide (DTAB) were obtained from
42 Tokyo Chemical Industry and used as received.

43 To modify KF with the surfactants, 0.2 g of KF were mixed with 2 cm³ of an aqueous
44 solution containing 0.46 mmol of the surfactant. After stirring for 2 h and standing for 24 h,
45 the organo-montmorillonites (denoted as O-KF and D-KF) were separated by filtration and
46 dried on air.

47 The adsorption of ANA on O-KF and D-KF was carried out as follows. First, 10 mg of
48 ANA were dissolved in 10 cm³ of ethanol. The ethanol solution of ANA was mixed with 0.2
49 g of O-KF or D-KF, and the dispersion was permitted to stand for 24 h in the dark. The
50 amount of the dye corresponded to 5 mass% of O-KF or D-KF. The sediment was collected
51 by filtration, dried at room temperature and ground to powder. The filtrates remained colored,

indicating that not all ANA molecules were adsorbed.

A mixture of water and ethanol (1:4 v/v) was also used instead of pure ethanol. The amount of the introduced dye was controlled by changing the volume of the added dye solution. A required volume of the ethanolic solution of ANA (1 mg/cm^3) was mixed with 20% (v/v) of water. The aqueous ethanolic solution of ANA was then mixed with 0.2 g of D-KF and maintained for 24 h in the dark. The solids were obtained by filtration and drying at room temperature. These samples are denoted as $\text{ANA}_{\text{w-}x}/\text{D-KF}$, where x represents the amount of the dye added to the sample (x mass% of D-KF) and ranged from 5 to 20 %. Except for $\text{ANA}_{\text{w-}20}/\text{D-KF}$, the filtrates of the samples were colorless, indicating that all of the ANA molecules were adsorbed onto D-KF.

Silica was used as the reference adsorbent. The silica was supplied from Catalysis Society of Japan (JRC-SIO-6, designated as SIO). SIO (0.2 g) was dispersed in 10 cm^3 of an ANA ethanolic solution containing 10 mg of ANA. The amount of ANA added was 5 % of silica. The ethanol was evaporated under an air stream in the dark at room temperature.

2.2 Measurements

XRD patterns were measured with the Rigaku MiniFlex X-ray diffractometer ($\text{CuK}\alpha$, step angle and scan speed 0.05° and $2^\circ/\text{min}$, 15mA, 30 kV). UV-Vis spectra were collected with the JASCO V-550 spectrophotometer. For the measurement of diffuse-reflectance spectra, the ISV-469 integrating sphere was equipped to the spectrometer. To investigate the light endurance of each sample, the samples were irradiated with visible light under ambient temperature and pressure. A 100 W halogen lamp (Schott Megalight 100) equipped with a 30 cm length flexible light guide was used as the visible light source. The powder samples were loaded in a plastic cell covered with a thin glass and placed 1.1 cm from the aperture of the light guide. The degree of the color fading was determined by the decrease of the absorption of ANA measured by the diffuse reflectance spectra. When the sample was irradiated in the absence of oxygen, the sample cell was packed in a transparent gas barrier film filled with nitrogen.

3. Results and discussion

3.1 Structural analysis

The XRD patterns of KF, O-KF and D-KF samples are illustrated in Fig. 1. The reflection of KF at around $2\theta = 7.4^\circ$ was assigned to the 001 reflection. The 001 reflection of O-KF and D-KF shifted to lower angle, indicating the increase of the basal spacing of O-KF and D-KF compared with the original KF. Considering the thickness of the silicate layer of KF as 0.96 nm, the interlayer distance of O-KF and D-KF was calculated to be 0.43 nm and 0.83 nm, respectively. These values were in good agreement with the reported value (Klapyta et al., 2001; Ogawa and Kuroda, 1997; Ogawa et al., 1992). Since the interlayer distance of O-KF (0.43 nm) corresponded to the size of the polar head group of the surfactant molecule, it was suggested that OTAB molecules formed a monolayer between the layers of KF. The interlayer distance of D-KF of 0.83 nm indicated bilayers of the surfactant ions in the interlayer space (Ogawa and Kuroda, 1997; Ogawa et al., 1992). The formation of the bilayers of DTAB makes the interlayer space more hydrophobic.

---Figure 1---

The dye was not adsorbed on KF itself, so that ANA/KF was not colored and the XRD patterns of KF and ANA/KF were identical. The XRD patterns of ANA/O-KF and ANA/D-KF were almost the same as those of O-KF and D-KF, respectively. Thus, the layered structure of the organo-montmorillonite was maintained after the adsorption of the

dye. Since the interlayer distance was not changed by the adsorption of the dye, the ANA molecules were probably dissolved in the *pseudo*-organic phase formed by the surfactant ions between the clay mineral layers.

3.2 UV-vis spectra

The diffuse-reflectance UV-Vis spectra normalized at the wavelength of maximal absorption are represented in Fig. 2. The solution of ANA exhibited absorption peaks at 455 nm and 482 nm together with a shoulder at 427 nm. ANA/SIO showed a single broad absorption band with λ_{max} at 430 nm. The fine structure observed in the spectrum of the ANA solution was lost, and the main peak shifted to shorter wavelength in ANA/SIO. These results suggested the aggregation of the adsorbed dye molecules. ANA/O-KF and ANA/D-KF exhibited a couple of peaks at 460, 490 nm and 462, 492 nm, respectively, with a shoulder band at around 435 nm. The spectral shape of ANA/O-KF and ANA/D-KF resembled that of the ANA solution suggesting that the ANA molecules were not aggregated but dispersed in ANA/O-KF and ANA/D-KF as in the solution. Compared with the spectrum of the dye molecules in the solution, the peaks were shifted by 5 to 10 nm to longer wavelengths. The

reason of the red shift in ANA/O-KF and ANA/D-KF was not sufficiently clarified yet. The spectral shift mechanism of carotenoids caused by the medium is still under investigation by several research groups, and the dispersion, polarization or interaction between charges was proposed (Renge and Sild, 2011; Yanagi et al., 2006). However, at least we can say that the ANA molecules were in an environment different from the solution. This suggests that the ANA molecules were surrounded by the alkyl chains of the surfactant ions between the clay mineral layers.

---Figure 2---

3.3 Light fastness

The spectral changes during irradiation are shown in Fig. 3. In every sample, the absorption of ANA decreased and the color was faded by the irradiation. The shape of each spectrum did not change drastically during the fading process, indicating that the process was not a photochemical conversion but a simple photo-degradation of the dye.

---Figure 3---

The time course of the absorption of the adsorbed ANA during irradiation is illustrated in

Fig. 4. Serious photo-fading was observed on ANA/SIO, and only 11% of the dye remained after 60 min irradiation. The light fastness of ANA/O-KF was not very good (24%). The most stable sample was ANA/D-KF showing considerable endurance against irradiation (55%).

---Figure 4---

3.4 Cause of the stability enhancement

To evaluate the effect of the atmospheric oxygen on the light fastness, ANA/D-KF and ANA/SIO were subjected to irradiation under nitrogen (Table 1). After 60 min irradiation, ANA/D-KF maintained 55% and 79% of the absorption of ANA under atmosphere and nitrogen, respectively. Thus, the light fastness of ANA/D-KF was slightly improved under nitrogen. While the retention of ANA absorption of ANA/SIO was only 11% in the air, the value was remarkably improved to 71% under nitrogen. Since ANA molecules are susceptible to oxidative degradation, the stabilization effect observed under nitrogen is interpreted as a hindrance from the contact of atmospheric oxygen. Therefore, we concluded that the ANA molecules in ANA/D-KF were protected from oxygen by the alkyl groups of the surfactant ions in the interlayer space. Although an organic phase generally tend to dissolve more

oxygen molecules, inhibition of the direct contact with gaseous oxygen significantly enhanced the stability of the incorporated dye.

---Table 1---

The stability of ANA/O-KF against irradiation was less than that of ANA/D-KF because the dye molecules in the interlayer space were less protected by the shorter alkyl chains. The monolayer arrangement of the octyl trimethylammonium ions in the interlayer space might be another reason (see section 3.1). Ogawa *et al.* also reported that anthracene or naphthalene was not clearly intercalated into montmorillonite modified by octyl trimethylammonium ions (Ogawa *et al.*, 1992).

3.5 Improvement in the dye adsorption

The color of ANA/D-KF was not strong because the amount of adsorbed ANA was not large. For the utilization as a colorant, the sample should exhibit a deeper color. Therefore, we tried to increase the amount of adsorbed dye by changing the solvent used in the dye adsorption procedure. Table 2 represents the absorbance of ANA adsorbed on D-KF from aqueous ethanolic solutions. The absorbance of the dye roughly corresponded to the amount

of the adsorbed dye. The addition of water considerably increased the amount of dye adsorbed. ANA_{w-5}/D-KF and ANA_{w-10}/D-KF adsorbed almost all ANA added since the filtrate was colorless. The absorbance of ANA_{w-5}/D-KF reached a 7 times higher value compared to ANA/D-KF. Since the ANA molecules preferred a hydrophobic environment, the increase in the polarity of the solvent pushed the ANA molecules toward the hydrophobized clay mineral layers.

---Table 2---

The absorbance of ANA_{w-10}/D-KF was nearly twice that of ANA_{w-5}/D-KF (Table 2). However, the absorbance of ANA_{w-20}/D-KF was almost the same as that of ANA_{w-10}/D-KF. In fact, on preparing ANA_{w-20}/D-KF, the filtrate remained colored, indicating that part of the added dye was not adsorbed. Therefore, the adsorption of ANA on D-KF was almost saturated in ANA_{w-10}/D-KF.

The light fastness of the ANA_{w-x}/D-KF series (Table 3) was not so different. ANA_{w-5}/D-KF and ANA_{w-10}/D-KF exhibited a little improved photostability compared with ANA/D-KF. This suggests that the ANA molecules were more deeply incorporated in the clay mineral interlayer because of the more polar solvent used in the adsorption process. The photostability of ANA in ANA_{w-20}/D-KF was lower than those of ANA_{w-5}/D-KF and

ANA_{w-10}/D-KF. Perhaps, the excess ANA molecules in ANA_{w-20}/D-KF were adsorbed on the external surfaces of the clay mineral particles, and such dye molecules were easily discolored by the oxidation under irradiation.

---Table 3---

4. Conclusion

As a hydrophobic natural dye, annatto dye was intercalated into montmorillonite if the interlayer space was hydrophobized by alkyl trimethylammonium ions. The annatto dye/organo-montmorillonites showed higher photostability than the pure annatto dye because the dye molecules were protected from the external oxygen by the layered structure of montmorillonite. Modification with dodecyl trimethylammonium ions was superior to octyl trimethylammonium ions in the improvement of the photostability of the annatto dye. Probably, the dodecyl trimethylammonium ions presented a more suitable environment for the adsorption of the dye. The amount of dye adsorbed was increased by using aqueous ethanolic solutions instead of pure ethanol in the adsorption process. The light fastness was not considerably influenced by the amount of the dye. The stabilized annatto dye is expected

205 to be widely used as an environmentally friendly colorant.

206

207 **Acknowledgment**

208 This work was financially supported by the Cosmetology Research Foundation and the
209 Ministry of Education, Culture, Sports, Science and Technology (Grant-in-Aid for Scientific
210 Research #22360330).

211

212 **References**

- 213 Balaswamy, K., Prabhakara Rao, P.G., Satyanarayana, A., Rao, D.G., 2006. Stability of bixin
214 in annatto oleoresin and dye powder during storage. *LWT - Food Sci. Technol.*, 39,
215 952-956.
- 216 Bauer, J., Behrens, P., Speckbacher, M. , Langhals, H., 2003. Composites of perylene
217 chromophores and layered double hydroxides: Direct synthesis, characterization, and
218 photo- and chemical stability. *Adv. Funct. Mater.*, 13, 241-248.
- 219 Bujdák, J., Iyi, N., Fujita, T., 2002. Aggregation and stability of 1,1'-diethyl-4,4'-cyanine dye
220 on the surface of layered silicates with different charge densities. *Colloids Surf. A*,
221 207, 207-214.
- 222 Celis, R., Trigo, C., Facenda, G., Hermosín, M.D.C., Cornejo, J., 2007. Selective
223 modification of clay minerals for the adsorption of herbicides widely used in olive
224 groves. *J. Agric. Food Chem.*, 55, 6650-6658.
- 225 Chakraborty, C., Dana, K., Malik, S., 2011. Intercalation of perylenediimide dye into ldh
226 clays: Enhancement of photostability. *J. Phys. Chem. C*, 115, 1996-2004.

227 Cruz-Guzman, M., Celis, R., Hermosin, M.C., Koskinen, W.C., Cornejo, J., 2005. Adsorption
 228 of pesticides from water by functionalized organobentonites. *J. Agric. Food Chem.*, 53,
 229 7502-7511.

230 Giustetto, R., Wahyudi, O., Corazzari, I., Turci, F., 2011. Chemical stability and dehydration
 231 behavior of a sepiolite/indigo maya blue pigment. *Appl. Clay Sci.*, 52, 41-50.

232 Groisman, L., Rav-Acha, C., Gerstl, Z., Mingelgrin, U., 2004. Sorption of organic compounds
 233 of varying hydrophobicities from water and industrial wastewater by long- and
 234 short-chain organoclays. *Appl. Clay Sci.*, 24, 159-166.

235 Klapysa, Z., Fujita, T., Iyi, N., 2001. Adsorption of dodecyl- and
 236 octadecyltrimethylammonium ions on a smectite and synthetic micas. *Appl. Clay Sci.*,
 237 19, 5-10.

238 Kohno, Y., Ito, M., Kurata, M., Ikoma, S., Shibata, M., Matsushima, R., Tomita, Y., Maeda,
 239 Y., Kobayashi, K., 2011. Photo-induced coloration of 2-hydroxychalcone in the clay
 240 interlayer. *J. Photochem. Photobiol. A*, 218, 87-92.

241 Kohno, Y., Kinoshita, R., Ikoma, S., Yoda, K., Shibata, M., Matsushima, R., Tomita, Y.,
 242 Maeda, Y., Kobayashi, K., 2009a. Stabilization of natural anthocyanin by intercalation
 243 into montmorillonite. *Appl. Clay Sci.*, 42, 519-523.

244 Kohno, Y., Totsuka, K., Ikoma, S., Yoda, K., Shibata, M., Matsushima, R., Tomita, Y.,
 245 Maeda, Y., Kobayashi, K., 2009b. Photostability enhancement of anionic natural dye
 246 by intercalation into hydrotalcite. *J. Colloid Interface Sci.*, 337, 117-121.
 247 Lagaly, G., Ogawa, M., Dékány, I., 2006. Clay mineral organic interactions. In: Bergaya, F.,
 248 Theng, B.K.G., Lagaly, G. (Eds.), *Handbook of Clay Science: Developments in Clay*
 249 *Science*, Volume 1. Elsevier, Amsterdam, pp. 309-377.
 250 Lyng, S.M.O., Passos, M., Fontana, J.D., 2005. Bixin and α -cyclodextrin inclusion complex
 251 and stability tests. *Process Biochem.*, 40, 865-872.
 252 Najar, S.V., Bobbio, F.O., Bobbio, P.A., 1988. Effects of light, air, anti-oxidants and
 253 pro-oxidants on annatto extracts (*bixa orellana*). *Food Chem.*, 29, 283-289.
 254 Ogawa, M., Kuroda, K., 1997. Preparation of inorganic-organic nanocomposites through
 255 intercalation of organoammonium ions into layered silicates. *Bull. Chem. Soc. Jpn.*,
 256 70, 2593-2618.
 257 Ogawa, M., Shirai, H., Kuroda, K., Kato, C., 1992. Solid-state intercalation of naphthalene
 258 and anthracene into alkylammonium-montmorillonites. *Clays Clay Miner.*, 40,
 259 485-490.

260 Prabhakara Rao, P.G., Jyothirmayi, T., Balaswamy, K., Satyanarayana, A., Rao, D.G., 2005.
 261 Effect of processing conditions on the stability of annatto (*bixa orellana* L.) dye
 262 incorporated into some foods. LWT - Food Sci. Technol., 38, 779-784.

263 Renge, I., Sild, E., 2011. Absorption shifts in carotenoids--influence of index of refraction
 264 and submolecular electric fields. J. Photochem. Photobiol. A, 218, 156-161.

265 Sasai, R., Iyi, N., Fujita, T., López Arbeloa, F., Martínez, V., Takagi, K., Itoh, H., 2004.
 266 Luminescence properties of Rhodamine 6G intercalated in surfactant/clay hybrid thin
 267 solid films. Langmuir, 20, 4715-4719.

268 Sasai, R., Iyi, N., Fujita, T., Takagi, K., Itoh, H., 2003. Synthesis of Rhodamine 6G/cationic
 269 surfactant/clay hybrid materials and its luminescent characterization. Chem. Lett., 32,
 270 550-551.

271 Seki, Y., Yurdakoç, K., 2005. Paraquat adsorption onto clays and organoclays from aqueous
 272 solution. J. Colloid Interface Sci., 287, 1-5.

273 Tong, D.S., Zhou, C.H., Lu, Y., Yu, H., Zhang, G.F., Yu, W.H., 2010. Adsorption of Acid
 274 Red G dye on octadecyl trimethylammonium montmorillonite. Appl Clay Sci., 50,
 275 427-431.

276 Yanagi, K., Miyata, Y., Kataura, H., 2006. Highly stabilized β -carotene in carbon nanotubes.

277 Adv. Mater., 18, 437-441.

278

279 Figure captions

280

281

282 **Figure 1.** XRD patterns of (a) KF, (b) O-KF and (c) D-KF.

283

284 **Figure 2.** (a) UV-Vis spectrum of the ethanolic solution of ANA and diffuse reflectance UV-Vis spectra of (b)

285 ANA/SIO, (c) ANA/O-KF and (d) ANA/D-KF.

286

287 **Figure 3.** Changes in the absorption spectra of (a) ANA/SIO, (b) ANA/O-KF and (c) ANA/D-KF during visible

288 light irradiation of 60 min.

289

290 **Figure 4.** Absorption of ANA-montmorillonites at $\lambda_{\max}$ during irradiation of 60 min. (a) ANA/SIO, (b)

291 ANA/O-KF and (c) ANA/D-KF. The ordinate is the ratio of the absorbance to the initial value.

292

Tables

Table 1. Light fastness of ANA/SIO and ANA/D-KF in the presence or absence of oxygen.

	ANA/D-KF	ANA/SIO
A/A_0 in the air ^a	0.55	0.11
A/A_0 under N ₂ ^a	0.79	0.71

^a Ratio of the absorption at $\lambda_{\max}$ before and after irradiation of 60 min.

Table 2. Changes in the absorbance of ANA by the solvent used in the adsorption step.

Sample	ANA/D-KF	ANA _{w-5} /D-KF	ANA _{w-10} /D-KF	ANA _{w-20} /D-KF
A_{460} ^a	0.08	0.54	1.01	1.12
$A_{460}/A_{460(\text{ANA/D-KF})}$ ^b	1	7	13	14

^a Absorbance at $\lambda_{\max}$ (460 nm).

^b Ratio of the absorbance of each sample to that of ANA/D-KF at $\lambda_{\max}$, reflecting the increase in the amount of adsorbed ANA.

Table 3. Light fastness of ANA/D-KF with various amounts of ANA loading.

Sample	ANA/D-KF	ANA _{w-5} /D-KF	ANA _{w-10} /D-KF	ANA _{w-20} /D-KF
A/A_0 ^a	0.55	0.65	0.67	0.57

^a Ratio of the absorption at $\lambda_{\max}$ before and after irradiation of 60 min.

Scheme 1

Figure 1

Figure 2

Figure 3

Figure 4