Remarkable Influence of Structures around Rhenium (V) Centers Constructed in Polyoxotungstates for Methanol Dehydrogenation under Visible Light Irradiation

著者	Kato Chika Nozaki, Nakayama Ryuta, Hattori Shota, Amano Hidekuni, Makino Yuki
journal or publication title	British Journal of Applied Science and Technology
volume	4
number	16
page range	2302-2319
year	2014-04-10
出版者	SCIENCEDOMAIN International
権利	(C) Copyright 2010-2014, SCIENCEDOMAIN international. All rights reserved. (C) 2014 Kato et al.; This is an Open Access article distributed under the terms of the Creative Commons AttributionLicense (http://creativecommons.org/licenses/by/3.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.
URL	http://hdl.handle.net/10297/7778

doi: 10.9734/BJAST/2014/9336

Remarkable Influence of Structures around Rhenium(V) Centers Constructed in Polyoxotungstates for Methanol Dehydrogenation under Visible Light Irradiation

Chika Nozaki Kato^{1,2*}, Ryuta Nakayama¹, Shota Hattori¹,
Hidekuni Amano¹ and Yuki Makino¹

¹Department of Chemistry, Faculty of Science, Shizuoka University, 836 Ohya, Suruga-ku, Shizuoka 422-8529, Japan

²Green Chemistry Research Division, Research Institute of Green Science and Technology, Shizuoka University, Ohya, Suruga-ku, Shizuoka 422-8529, Japan

ABSTRACT

The synthesis and characterization of α_1 -Dawson-type mono-rhenium(V)-substituted polyoxotungstate, $[\alpha_1\text{-P}_2\text{W}_{17}\text{Re}^{\text{V}}\text{O}_{62}]^{7-}$ (**1**), are described. The dimethylammonium salt of **1**, $[\text{Me}_2\text{NH}_2]_7[\alpha_1\text{-P}_2\text{W}_{17}\text{Re}^{\text{V}}\text{O}_{62}]\cdot 9\text{H}_2\text{O}$ (**Me₂NH₂-1**), was obtained as analytically pure homogeneous black-blue crystals by reacting mono-lacunary α_1 -Dawson polyoxotungstate with $[\text{Re}^{\text{IV}}\text{Cl}_6]^{2-}$ in $\text{CH}_3\text{COOH}/\text{CH}_3\text{COOLi}$ buffer, followed by crystallization via a vapor diffusion from acetonitrile/ethanol. Characterization was also accomplished by X-ray crystallography, elemental analysis, TG/DTA, FTIR, UV-vis, and solution ^{31}P NMR spectroscopy; these results showed that the polyoxoanion **1** was a monomeric α -Dawson structure, in which the rhenium(V) ion was coordinated to the monovacant site of $[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]^{9-}$, resulting in an overall C_1 symmetry. The polyoxoanion **1**, $[\text{O}\{\text{Re}^{\text{V}}(\text{OH})(\alpha_2\text{-P}_2\text{W}_{17}\text{O}_{61})\}_2]^{14-}$ (**2**), and $[\alpha\text{-PW}_{11}\text{Re}^{\text{V}}\text{O}_{40}]^{4-}$ (**3**) showed the hydrogen evolution from methanol under visible light irradiation (≥ 400 nm) in the presence of titanium dioxide. The activities were remarkably depended on the rhenium(V) sites in **1** – **3**; polyoxoanion **2** possessing the dirhenium(V)-oxido-bridged site showed the highest activities among these complexes.

Keywords: Rhenium(V); polyoxometalate; crystal structure; photocatalyst; methanol dehydrogenation

1. INTRODUCTION

Since the Honda–Fujishima effect, i.e., photoinduced water splitting by titanium dioxide (TiO_2) and platinum electrodes was first reported, various photocatalytic materials have been investigated, because the generated hydrogen (H_2) is a clean and renewable fuel source [1–6]. Although TiO_2 is one of the most promising photocatalysts owing to its sufficient photostability, commercial availability, easy preparation, and its high activity for a wide range of photocatalytic reactions, it absorbs only ultraviolet (UV) light because of its wide band gap (varying from 3.0 to 3.2 eV, depending on the crystal structure); this limits the use of sunlight as an irradiation source in photocatalytic reactions [7,8]. One of the most powerful

* Tel.: +81 54 238 4764; fax: +81 54 237 3384.
E-mail address: sckatou@ipc.shizuoka.ac.jp.

approaches to developing visible-light-driven TiO₂ materials is surface modification. To date, numerous TiO₂ materials have been prepared by sensitizing transition metals [8–16], organic dyes [4, 7, 17–22], and organic moieties [23–29], and they show high activities in the presence of cocatalysts for various photoreactions. Although these are excellent studies, there is still room for improving TiO₂-based photocatalytic systems by including a sensitizer and a cocatalyst.

Polyoxometalates have attracted considerable attention because of their high versatility and unique range of properties; these include catalytic and biological activities and/or photochemical, electrochromic, and magnetic properties [30–32]. Photocatalytic systems constructed using TiO₂ and polyoxometalates, e.g., PW₁₂O₄₀³⁻, PMo₁₂O₄₀³⁻, GeW₁₂O₄₀⁴⁻, SiW₁₂O₄₀⁴⁻, BW₁₂O₄₀⁵⁻, α -P₂W₁₈O₆₂⁶⁻, and α_2 -P₂W₁₇O₆₁¹⁰⁻, also exhibit efficient photocatalytic activities under visible light irradiation; however, they required a pretreatment by UV irradiation to form “heteropoly blue” species, and large amounts of cocatalyst [33–38]. Recently, we demonstrated the catalytic activities of α_2 -Dawson and Keggin rhenium(V)-coordinated polyoxotungstates, [O{Re^V(OH)(α_2 -P₂W₁₇O₆₁)₂}₂]¹⁴⁻ and [α -PW₁₁Re^VO₄₀]⁴⁻, in H₂ evolution from water vapor and an aqueous solution of EDTA·2Na (ethylenediamine tetraacetic acid disodium salt) in the presence of TiO₂ under visible light irradiation (≥ 400 and ≥ 420 nm) [39, 40]. In this system, the pretreatment by UV irradiation was not necessary, and the rhenium compounds exhibited high photocatalytic activities without cocatalyst. Thus, the rhenium(V)-coordinated polyoxometalates were useful compounds for development of visible-light-driven TiO₂-based photocatalyst; however, the structure dependence of rhenium(V) sites constructed in polyoxometalate is still open to discussion because significant [α -PW₁₁Re^VO₄₀]⁴⁻ decomposition was observed in an EDTA·2Na aqueous solution during light irradiation.

In this study, we first synthesized α_1 -Dawson-type mono-rhenium(V)-substituted polyoxotungstate [Me₂NH₂]₇[α_1 -P₂W₁₇Re^VO₆₂]₂·9H₂O (**Me₂NH₂-1**) and characterized it using X-ray crystallography, elemental analysis, thermogravimetric analysis/differential thermal analysis (TG/DTA), and Fourier-transform infrared (FTIR), UV-visible, and solution ³¹P nuclear magnetic resonance (NMR) spectroscopies. To investigate the structure dependence of rhenium(V) sites for the photocatalytic reactions, we focused on the methanol dehydrogenation catalyzed by **Me₂NH₂-1**, K₁₄[O{Re^V(OH)(α_2 -P₂W₁₇O₆₁)₂}₂]₂·21H₂O (**K-2**), and [Me₂NH₂]₄[α -PW₁₁Re^VO₄₀] (**Me₂NH₂-3**) under visible light irradiation (≥ 400 nm) in the presence of TiO₂. Here, we report full details of the synthesis and molecular structure of complex **1**, and demonstrate the photocatalytic activities and stabilities of complexes **1** – **3**.

2. EXPERIMENTAL DETAILS

2.1 Materials

K₁₄[O{Re^V(OH)(α_2 -P₂W₁₇O₆₁)₂}₂]₂·21H₂O (**K-2**) [40], [Me₂NH₂]₄[α -PW₁₁Re^VO₄₀] (**Me₂NH₂-3**) [40], K₉[α_1 -LiP₂W₁₇O₆₁]₂·22H₂O [41], and K₁₀[α_2 -P₂W₁₇O₆₁]₂·27H₂O [42] were synthesized as described in the literatures. The number of solvated water molecules was determined by TG/DTA analyses. K₂[Re^{IV}Cl₆] was purified by the reprecipitation from water/ethanol. TiO₂ (anatase/rutile = 80/20; 99.9%; -5 μ m) was obtained from Wako Pure Chemical Industries, Ltd. Other reagents and solvents were obtained and used as received from commercial sources.

2.2 Instrumentation/analytical procedures

The elemental analysis was carried out by using a Mikroanalytisches Labor Pascher instrument (Remagen, Germany). The samples were dried overnight at room temperature under 10^{-3} – 10^{-4} Torr vacuum before analysis. The infrared spectra were recorded on a Parkin Elmer Spectrum100 FT-IR spectrometer in KBr disks at room temperature. Thermogravimetric (TG) and differential thermal analyses (DTA) data were obtained using a Rigaku Thermo Plus 2 series TG/DTA TG 8120. The TG/DTA measurements were performed in air with a temperature increase of 4 °C per min between 20 and 500 °C. The ^{31}P - $\{^1\text{H}\}$ (242.95 MHz) nuclear magnetic resonance (NMR) spectra in solutions were recorded in 5-mm outer diameter tubes on a JEOL ECA-600 NMR spectrometer (Shizuoka University). The ^{31}P NMR spectra were measured in $\text{CH}_3\text{COOLi}\cdot\text{D}_2\text{O}$ and D_2O with reference to an external standard of 85% H_3PO_4 in a sealed capillary. Chemical shifts were reported as negative on the δ scale for resonance upfield of H_3PO_4 (δ 0). Solution UV-vis spectra were recorded on a Perkin-Elmer Spectrum Lambda 650 spectrophotometer. The positions of sharp bands were automatically determined by software of UV-visible spectrometer, and those of broad bands were picked up at the highest values in the ASCII files. Potentiometric titration was carried out with 0.841 mmol/L tetra-*n*-butylammonium hydroxide as a titrant under argon atmosphere [43]. The compound **Me₂NH₂-1** (4.12 μmol) was dissolved in acetonitrile (20 mL) at 25 °C, and the solution was stirred for approximately 5 min. The titration data were obtained with a pH meter (Mettler Toledo). Data points were obtained in millivolt. A solution of tetra-*n*-butylammonium hydroxide (0.841 mmol/L) was syringed into the suspension in 0.20-equivalent intervals.

2.3 Synthesis of **[Me₂NH₂]₇[α_1 -P₂W₁₇Re^VO₆₂]-9H₂O (Me₂NH₂-1)**

A solution of $\text{K}_2[\text{Re}^{\text{IV}}\text{Cl}_6]$ (0.365 g; 0.765 mmol) dissolved in 10 mL of water was added to a solution of $\text{K}_9[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]\cdot 22\text{H}_2\text{O}$ (1.865 g; 0.379 mmol) dissolved in 25 mL of $\text{CH}_3\text{COOH}/\text{CH}_3\text{COOLi}$ buffer solution (pH = 4.5) at 25 °C. After stirring for 4 h at 25 °C in the dark, a solid $[\text{Me}_2\text{NH}_2]\text{Cl}$ (3.114 g; 38.3 mmol) was added to the solution, followed by stirring overnight at 25 °C. A deep blue-colored precipitate was collected using a membrane filter (JG 0.2 μm). At this stage, a crude product was obtained in 1.74 g yield. For crystallization, the crude product (1.74 g) was dissolved in 350 mL of acetonitrile at 25 °C; the resulting solution was filtered through a folded filter paper (Whatman #5). Black block crystals were obtained via vapor diffusion from methanol at 25 °C. The yield was 0.464 g. The percent yield was calculated on the basis of $[\text{mol of Me}_2\text{NH}_2\text{-1}]/[\text{mol of K}_9\text{Li}[\alpha_1\text{-P}_2\text{W}_{17}\text{O}_{61}]\cdot 22\text{H}_2\text{O}] \times 100$ and was 25%. Elemental analysis results showed C, 3.57; H, 1.42; N, 2.05; P, 1.28; Re, 4.00; W, 66.0; K, 0.03; Li, <0.01%. Calculations for $[(\text{CH}_3)_2\text{NH}_2]_7[\alpha_1\text{-P}_2\text{W}_{17}\text{ReO}_{62}]\cdot x\text{H}_2\text{O}$ ($x = 2$) = $\text{H}_{60}\text{C}_{14}\text{N}_7\text{O}_{64}\text{P}_2\text{ReW}_{17}$: C, 3.56; H, 1.28; N, 2.08; P, 1.31; Re, 3.94; W, 66.2%. A weight loss of 2.54% was observed during overnight drying at room temperature under 10^{-3} – 10^{-4} torr before analysis, suggesting seven water molecules (2.60%). TG/DTA under atmospheric conditions showed a weight loss of 12.2% below 500 °C with an exothermic point at 381.1 °C. A clear endothermic point was not observed; calculations showed 10.0% for the sum of seven dimethylammonium ions and nine water molecules. IR (KBr disk) results in the 1300 – 400 cm^{-1} region (polyoxometalate region) showed: 1094m, 1077m, 1014w, 959s, 918m, 823m, 776m, and 733m cm^{-1} . ^{31}P NMR (0.285 M $\text{CH}_3\text{COOLi}\cdot\text{D}_2\text{O}$ solution, 22.3 °C): δ -12.1, -12.4. UV-visible absorption (in H_2O , 1.0×10^{-5} and 1.0×10^{-4} M) showed: λ 263 nm (ϵ $4.4 \times 10^4 \text{ M}^{-1}\text{cm}^{-1}$), λ 310 nm (ϵ $1.8 \times 10^4 \text{ M}^{-1}\text{cm}^{-1}$), and λ 468 nm (ϵ $3.7 \times 10^3 \text{ M}^{-1}\text{cm}^{-1}$).

2.4 X-ray crystallography

A black block crystal of **Me₂NH₂-1** ($0.180 \times 0.050 \times 0.040 \text{ mm}^3$) was mounted in a loop. Data were collected by a Rigaku Mercury70 diffractometer using monochromated Mo K α radiation ($\lambda = 0.71070 \text{ \AA}$) at 113 K. Data were collected and processed using CrystalClear

software for Windows. The structural analysis was performed using the CrystalStructure software for Windows. All structures were solved by SHELXS-97 (direct methods) and refined by SHELXL-97 [44]. Since one rhenium atom was disordering over twelve tungsten sites (W(4) – W (15)) in polyoxoanion **1**, the occupancies for the rhenium and tungsten sites were fixed at 1/12 and 11/12 throughout the refinement. The seven dimethylammonium ions and some acetonitrile and ethanol molecules were observed; however, no acetonitrile and ethanol solvent molecules were observed by elemental analysis and ¹H NMR spectroscopy. Thus, the solvent molecules evaporate gradually when crystals are removed from acetonitrile solution. Accordingly, the residual electron density was removed using the SQUEEZE routine in PLATON [45].

2.5 X-ray crystallography

C₁₄H₆₀N₇O₆₄P₂ReW₁₇; M = 4724.24, *triclinic*, space group *P*-1 (#2), *a* = 13.317(5) Å, *b* = 13.377(4) Å, *c* = 24.248(9) Å, α = 79.24(2)^o, β = 79.78(2)^o, γ = 68.28(2)^o, *V* = 3914(3) Å³, *Z* = 2, *D_c* = 4.008 g/cm³, μ (Mo-K α) 265.749 cm⁻¹. *R*₁ = 0.0678 (*I* > 2 σ (*I*)), *wR*₂ = 0.1837 (for all data). GOF = 1.079 (26430 total reflections, 14529 unique reflections where *I* > 2 σ (*I*)). CCDC reference number 968914 contains the supplementary crystallographic data for this paper. These data can be obtained free of charge at www.ccdc.cam.ac.uk/conts/retrieving.html [or from Cambridge Crystallographic Data Centre, 12 Union Road, Cambridge CB2 1EZ, UK; Fax: +44-1223-336-033; E-mail: deposit@ccdc.cam.ac.uk].

2.6 Catalytic reaction experiments

For methanol dehydrogenation, TiO₂ (anatase/rutile = 80/20) (200 mg) and rhenium compounds were suspended in 10 mL of methanol. The mixture was placed into a glass reaction vessel; this was connected to a Pyrex conventional closed gas circulation system (245.5 cm³). The compounds **Me₂NH₂-1** (2.8 – 9.4 mg; 0.6 – 1.9 μ mol of Re), **K-2** (2.4 – 10 mg; 0.6 – 2.0 μ mol of Re), and **Me₂NH₂-3** (1.8 – 6.1 mg; 0.6 – 2.0 μ mol of Re) were used for the photoreactions. The photoreaction was started by light irradiation with a 300 W Xe lamp equipped with a cut-off filter (λ ≥ 400 nm). H₂, O₂, CO, and CH₄ were analyzed by GC (TCD, Molecular Sieve 5A stainless columns): the samples were assigned after they were compared with authentic samples analyzed under the same conditions. Turnover number (TON) was calculated as 2[hydrogen evolved (mol)]/[Re atoms (mol)]. Formaldehyde was observed by the published method [46].

3. RESULTS AND DISCUSSION

3.1 Synthesis and molecular structure of [Me₂NH₂]₇[α ₁-P₂W₁₇Re^VO₆₂] $\cdot$ 9H₂O (**Me₂NH₂-1**)

The dimethylammonium salt of **1**, [Me₂NH₂]₇[α ₁-P₂W₁₇Re^VO₆₂] $\cdot$ 9H₂O (**Me₂NH₂-1**), was synthesized by the direct reaction of 2 equiv of K₂Re^{IV}Cl₆ with mono-lacunary α ₁-Dawson polyoxotungstate, [α ₁-LiP₂W₁₇O₆₁]⁹⁻, in a CH₃COOH/CH₃COOLi aqueous buffer solution (pH = 4.5) under air, at 25 °C; this was followed by addition of excess Me₂NH₂Cl, forming a dark blue precipitate. The formation of polyoxoanion **1** is represented by the ionic balance shown in Eq. 1, in which rhenium(IV) is oxidized to rhenium(V), as observed for compounds **K-2** and **Me₂NH₂-3** [39,40]. Notably, polyoxoanion **1** was gradually isomerized to the α ₂-isomer during the reaction of K₂Re^{IV}Cl₆ with [α ₁-LiP₂W₁₇O₆₁]⁹⁻ in aqueous solution; the CH₃COOH/CH₃COOLi aqueous buffer solution is therefore indispensable in inhibiting isomerization, as observed for [α ₁-LiP₂W₁₇O₆₁]⁹⁻ [41]. In addition, the reaction temperature

should be kept at ca. 25 °C, even in a buffer solution, because heat treatment accelerated the isomerization. An excess of $\text{K}_2\text{Re}^{\text{IV}}\text{Cl}_6$ was therefore required to complete (accelerate) the coordination of rhenium ion to the mono-vacant site of $[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]^{9-}$. For purification, the unreacted $\text{K}_2\text{Re}^{\text{IV}}\text{Cl}_6$ was completely removed by crystallization via vapor diffusion from acetonitrile/ethanol.

The sample was dried overnight at room temperature under a vacuum of $10^{-3} - 10^{-4}$ Torr for elemental analysis. The elemental results for C, H, N, Re, P, and W were in good agreement with the calculated values for the chemical formula of **Me₂NH₂-1** with two hydrated water molecules. The presence of seven dimethylammonium ions suggested that the oxidation state of the rhenium site was 5+; this was also supported by the fact that no protonation was observed in potentiometric titration with tetra-*n*-butylammonium hydroxide in acetonitrile. The weight loss observed during drying before analysis was 2.54% for **Me₂NH₂-1**, corresponding to seven weakly solvated or adsorbed water molecules. However, during TG/DTA under atmospheric conditions, a weight loss of 12.2% was observed below 500 °C, corresponding to seven dimethylammonium ions and nine water molecules.

The X-ray structural analysis of crystalline $[\text{Me}_2\text{NH}_2]_7[\alpha_1\text{-P}_2\text{W}_{17}\text{Re}^{\text{V}}\text{O}_{62}] \cdot 2\text{H}_2\text{O}$ revealed that the molecular structure of **1** was identical to that of a monomeric α -Dawson polyoxotungstate, $[\alpha\text{-P}_2\text{W}_{18}\text{O}_{62}]^{6-}$, as shown in Figure 1. The bond lengths and bond angles are shown in Appendix. As a result of the high-symmetry space group, 12 tungsten sites [W(4) – W(15)] were disordered and a mono-rhenium-substituted site was not identified, as observed for $[\text{W}_9\text{ReO}_{32}]^{5-}$ [47] and $[\alpha\text{-PW}_{11}\text{Re}^{\text{V}}\text{O}_{40}]^{5-}$ [48]. Some ethanol and acetonitrile molecules were observed in a single crystal of **Me₂NH₂-1**; however, no acetonitrile and ethanol solvent molecules were observed by elemental analysis and ^1H NMR spectroscopy. The solvent molecules therefore evaporate gradually when the crystals are removed from acetonitrile solution.

The FTIR spectrum of compound **Me₂NH₂-1**, which was obtained using a KBr disk, is shown in Figure 2. The positions of all the bands (1094, 1077, 1014, 959, 918, 823, 776, and 733 cm^{-1}) in the polyoxoanion region of this compound are characteristic of polyoxoanions; however, they were different from those for $[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]^{9-}$ (1122, 1092, 1011, 944, 908, 828, 783, and 744 cm^{-1}), **K-2** (1091, 1018, 955, 910, and 788 cm^{-1}), and $[\alpha\text{-P}_2\text{W}_{18}\text{O}_{62}]^{6-}$ (1091, 1020, 958, 912, 777, and 528 cm^{-1}). This suggests coordination of a rhenium(V) ion in the monovacant site of $[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]^{9-}$.

The ^{31}P NMR spectrum in $\text{CH}_3\text{COOLi}\text{-D}_2\text{O}$ solution of **Me₂NH₂-1** showed a clear two-line spectrum, with signals at -12.1 ppm and -12.4 ppm, as shown in Figure 3(a). The signals were shifted compared with those of $[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]^{9-}$ (-8.7 ppm and -13.0 ppm) and $[\alpha\text{-P}_2\text{W}_{18}\text{O}_{62}]^{6-}$ (-12.8 ppm), indicating complete coordination of rhenium atom to monovacant site of $[\alpha_1\text{-LiP}_2\text{W}_{17}\text{O}_{61}]^{9-}$, as shown in Figure 1. No contamination of the sample by polyoxoanion **2** (-11.9 ppm and -12.9 ppm in D_2O) was observed; however, polyoxoanion **1** gradually isomerized to polyoxoanion **2** in aqueous solution. The ^{183}W NMR spectrum of **Me₂NH₂-1** was failed to obtain because of its low solubility in water and acetonitrile.

The UV-visible spectrum of **Me₂NH₂-1** in water showed four absorption bands, at 263 ($\epsilon 4.4 \times 10^4 \text{ M}^{-1}\text{cm}^{-1}$), 310 ($\epsilon 1.8 \times 10^4 \text{ M}^{-1}\text{cm}^{-1}$), 468 ($\epsilon 3.7 \times 10^3 \text{ M}^{-1}\text{cm}^{-1}$), and 613 nm ($\epsilon 5.2 \times 10^3 \text{ M}^{-1}\text{cm}^{-1}$), as shown in Figure 4. The bands at 263 nm and 310 nm were assigned to the charge transfer (CT) band of W-O bonds. The two bands at 468 and 613 nm were assigned to the $\text{Re}^{\text{V}} \rightarrow \text{W}^{\text{VI}}$ intervalence charge transfer (IVCT) band and the *d-d* band of the

243 rhenium(V) atom, respectively [39,40]. It was noted that the bands at 468 nm and 613 nm
 244 for **Me₂NH₂-1** were significantly broader rather than those for **K-2** and **Me₂NH₂-3**, and the
 245 positions were blue-shifted compared with those for **K-2** (496 nm and 737 nm) and **Me₂NH₂-**
 246 **3** (513 nm and 698 nm); this also suggested coordination of the rhenium(V) ion to the
 247 monovacant site in [α_1 -LiP₂W₁₇O₆₁]⁹⁻.
 248

249
 250
 251 **Fig. 1. (a) The molecular structure (ORTEP drawing) of**
 252 **polyoxoanion 1 with all atom numberings and (b) polyhedral**
 253 **representation of polyoxoanion 1. In (b), WO₆ and ReO₆ units are**
 254 **represented by the white and purple octahedra, respectively. The**
 255 **internal PO₄ units are represented by the red tetrahedra.**
 256

257
 258 **Fig. 2. FTIR spectrum as a KBr disk of Me₂NH₂-1.**

259

260

261

262

263

264

265

266

Fig. 3. ^{31}P NMR spectra in 0.285 M $\text{CH}_3\text{COOLi-D}_2\text{O}$ of (a) $\text{Me}_2\text{NH}_2\text{-1}$ and (b) after photoreaction. The spectrum was referenced to an external standard of 85% H_3PO_4 in a sealed capillary. In (b), $\text{Me}_2\text{NH}_2\text{-1}$ (50 mg) and TiO_2 (500 mg) were suspended in methanol (25 mL), and they were irradiated under the visible light (≥ 400 nm) for 6 h.

267

268

269

Fig. 4. UV-visible spectra in H_2O of $\text{Me}_2\text{NH}_2\text{-1}$ (1.0×10^{-5} M) at 200 – 800 nm. Inset: 400 – 800 nm (1.0×10^{-4} M).

3.2 Catalytic activities in methanol dehydrogenation catalyzed by rhenium(V)-coordinated polyoxotungstates in the presence of TiO₂ under visible-light irradiation (≥ 400 nm)

Methanol dehydrogenation catalyzed by rhenium(V)-coordinated polyoxotungstates at 25 °C in the presence of TiO₂ under light irradiation (≥ 400 nm) was investigated; the results are summarized in Table 1. Hydrogen was evolved from methanol catalyzed by **Me₂NH₂-1**, **K-2**, and **Me₂NH₂-3**. Formaldehyde was also observed; while, O₂, CO, and CH₄ were not observed. The three rhenium(V) compounds were hardly soluble in methanol. When a suspension of **K-2** (50 mg) and TiO₂ (200 mg) in methanol (25 mL) was irradiated under visible light (≥ 400 nm) for 6 h, followed by filtration through a membrane filter (JG 0.2 μ m), UV-vis spectrum of the filtrate showed a small band at around 220 nm due to a charge transfer band of W^{VI}-O; however, this was significantly smaller than that in 30 mM EDTA·2Na aqueous solution (25 mL) under the same reaction conditions, as shown in Figure 5. Even when the cesium salts of **1** – **3** were used as catalysts, a slight leaching into methanol was observed. These results suggested that the rhenium(V) compounds were predominantly active in the solid state under the present reaction conditions. The initial dehydrogenation rates with **Me₂NH₂-1** and **Me₂NH₂-3** were slow; while, no induction period was observed for **K-2**, as shown in Figure 6. The colors of these materials changed from white-purple to blue during the reactions; however, the blue color disappeared and the photoreactions stopped when visible light irradiation stopped.

Fig. 5. UV-visible spectra of K-2 at 200 – 800 nm.
K-2 (50 mg) and TiO₂ (500 mg) were suspended in (a) 30 mM EDTA·2Na aqueous solution (25 mL) and (b) methanol (25 mL), and they were irradiated under the visible light (≥ 400 nm) for 6 h at 25 °C. After a filtration through a membrane filter (JG 0.2 μ m), UV-vis spectra of the filtrates were observed, respectively.

In control experiments, hydrogen was not detected when the reaction was catalyzed by TiO₂. The rhenium(V)-coordinated polyoxotungstates showed no reaction in the absence of TiO₂. K₁₀[α_2 -P₂W₁₇O₆₁] $\cdot$ 27H₂O also showed no reaction even in the presence of TiO₂. A combination of rhenium(V)-coordinated sites in the polyoxotungstates and TiO₂ was therefore necessary, as reported for photoreactions using an EDTA·2Na aqueous solution in

the presence of TiO₂ under light irradiation (≥ 400 nm) [39,40]. For the three rhenium compounds (1.0 μ mol of Re), the evolved amounts of H₂ after 6 h were 17.7, 206, and 72.4 μ mol [the turnover numbers (TONs) were 35, 412, and 145, respectively]; these results showed that **K-2** had the highest activity among these samples under the present reaction conditions. Even for 0.6 and 2.0 μ mol of Re, **K-2** exhibited the highest activities; however, the TONs decreased with increasing concentration of rhenium(V) atoms. When the cesium salts of **2** and **3**, Cs₁₄[O{Re(OH)(α_2 -P₂W₁₇O₆₁)₂}] (**Cs-2**) [40] and Cs_{3.5}H_{0.5}[PW₁₁ReO₄₀] (**Cs-3**) [40], were used as catalysts, the activities decreased compared with those of **K-2** and **Me₂NH₂-3**; however, the activities of **Cs-2** were higher than those of **Cs-3**. These results suggested that the structure dependence was not influenced by the counter ion.

Table 1. Hydrogen evolution from methanol catalyzed by rhenium(V)-coordinated polyoxometalates under visible light irradiation^a

Catalyst (μ mol of rhenium atom)	H ₂ [μ mol]	TON ^b
Me₂NH₂-1 /TiO ₂ (0.6)	10.8	36
Me₂NH₂-1 /TiO ₂ (1.0)	17.7	35
Me₂NH₂-1 /TiO ₂ (1.9)	29.9	31
K-2 /TiO ₂ (0.6)	103	345
K-2 /TiO ₂ (1.0)	206	412
K-2 /TiO ₂ (2.0)	116	116
Me₂NH₂-3 /TiO ₂ (0.6)	42.4	141
Me₂NH₂-3 /TiO ₂ (1.0)	72.4	145
Me₂NH₂-3 /TiO ₂ (2.0)	34.0	34

^a = Reaction conditions are as follows: methanol (10 mL), **Me₂NH₂-1** (0.6 – 1.9 μ mol of Re), **K-2** (0.6 – 2.0 μ mol of Re), and **Me₂NH₂-3** (0.6 – 2.0 μ mol of Re), titanium dioxide (anatase/rutile = 80/20) (200 mg), reaction time 6 h, light (≥ 400 nm), 25 °C

^b = Turnover number (TON) was calculated as 2[H₂ evolved (mol)] per [Re atoms (mol)]

The stabilities of polyoxoanions **1** – **3** during methanol dehydrogenation were determined by ³¹P NMR spectroscopy, as follows: TiO₂ (500 mg) and the rhenium compounds (50 mg) were suspended in 25 mL of methanol. After light irradiation for 6 h, the solids were collected using a membrane filter (JG 0.2 μ m). The solids were suspended in 10 mL of water, and the filtrates, containing dissolved polyoxoanions **1** – **3**, were evaporated to dryness at 40 °C. As shown in Figures 3(b) and 7, the ³¹P NMR spectra in CH₃COOLi-D₂O of **1**, and in D₂O of **2** and **3**, were the same as those of the as-prepared samples. This showed that these compounds did not decompose or isomerize during methanol dehydrogenation under light irradiation. It was clear that the rhenium(V) sites in polyoxometalates significantly affected the photocatalytic activities, and the dirhenium(V)-oxido-bridged site in **2** exhibited the highest activity among these three samples under the present reaction conditions.

338

339

340

341

342 **Fig. 6. Time course for methanol dehydrogenation catalyzed by (a) Me₂NH₂-1 (1.0 μmol**

343 **of Re), (b) K-2 (1.0 μmol of Re), and (c) Me₂NH₂-3 (1.0 μmol of Re). In this system, the**

344 **three polyoxotungstates and TiO₂ were suspended in methanol, and the visible light**

345 **(≥400 nm) was irradiated for 6 h at 25 °C. Reaction conditions are shown in Table 1.**

Fig. 7. ^{31}P NMR spectra in D_2O of (a) K-2 and (b) $\text{Me}_2\text{NH}_2\text{-3}$ after photoreactions. The rhenium compounds (50 mg) and TiO_2 (500 mg) were suspended in methanol (25 mL), and they were irradiated under the visible light (≥ 400 nm) for 6 h.

4. CONCLUSION

A rhenium(V) complex composed of mono-lacunary α_1 -Dawson polyoxotungstate was presented. We successfully obtained single crystals of dimethylammonium salt $[\text{Me}_2\text{NH}_2]_7[\alpha_1\text{-P}_2\text{W}_{17}\text{Re}^{\text{VO}}_{62}]\cdot 9\text{H}_2\text{O}$ (**Me₂NH₂-1**) by reacting hexachlororhenate with a mono-lacunary α_1 -Dawson polyoxoanion in $\text{CH}_3\text{COOH}/\text{CH}_3\text{COOLi}$ buffer, followed by crystallization via vapor diffusion from acetonitrile/ethanol. The characterization of compound **Me₂NH₂-1** was accomplished by X-ray structure analysis, elemental analysis, TG/DTA, FTIR, UV-visible, and solution ^{31}P NMR spectroscopy. For methanol dehydrogenation under visible light irradiation (≥ 400 nm) in the presence of TiO_2 , the molecular structures of three rhenium(V) compounds were stable during the photoreactions, and the dirhenium(V)-oxido-bridged site in **2** exhibited the most effective activities compared with those of the mono-rhenium(V)-substituted sites in **1** and **3**.

ACKNOWLEDGEMENTS

This work was supported by a Grant-in-Aid for Scientific Research C (No. 23550150) of the Ministry of Education, Culture, Sports, Science and Technology, Japan.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Fujishima A, Honda K. Electrochemical photolysis of water at a semiconductor electrode. *Nature*. 1972; 238 37-38.
2. Schiavello M, editor. *Heterogeneous photocatalysis*. Chichester: John Wiley & Sons; 1997.
3. Fujishima A, Hashimoto K, Watanabe T. *TiO₂ Photocatalysis: Fundamentals and applications*. Tokyo: BKC Inc; 1999.
4. Abe R, Recent progress on photocatalytic and photoelectrochemical water splitting under visible light irradiation. *J Photochem Photobiol C: Photochem Rev*. 2010; 11 179-209.
5. Maeda K, Domen K. Photocatalytic water splitting: recent progress and future challenges. *J Phys Chem Lett*. 2010; 1 2655-2661.
6. Maeda K, Domen K. Surface nanostructures in photocatalysts for visible-light-driven water splitting. *Top Curr Chem*. 2011; 303 95-119, and references therein.
7. Chatterjee D. Effect of excited state redox properties of dye sensitizers on hydrogen production through photo-splitting water over TiO₂ photocatalyst. *Catal Commun*. 2010; 11 336-339.
8. Zielińska-Jurek A, Kowalska E, Sobczak JW, Lisowski W, Ohtani B, Zaleska A. Preparation and characterization of monometallic(Au) and bimetallic(Ag/Au)-modified titania photocatalysts activated by visible light. *Appl Catal B: Environ*. 2011; 101 504-514.
9. Sonawane RS, Dongare MK. Sol-gel synthesis of Au/TiO₂ thin films for photocatalytic degradation of phenol in sun light. *J Mol Catal A: Chem*. 2006; 243 68-76.
10. Chuang H, Chen D. Fabrication and photocatalytic activities in visible light and UV light regions of Ag@TiO₂ nanoparticles. *Nanotechnology* 2009; 20 105704-105714.
11. Li FB, Li XZ. Photocatalytic properties of gold/gold ion-modified titanium dioxide for waste water treatment. *Appl Catal A: Gen*. 2002; 228 15-27.
12. Seery MK, George R, Floris P, Pillai SC. Silver doped titanium dioxide nanomaterials for enhanced visible light photocatalysis. *J Photochem Photobiol A Chem*. 2007; 189 258-263.
13. Ishibai Y, Sato J, Nishikawa T, Miyagishi S. Synthesis of visible-light-active TiO₂ photocatalyst with Pt-modification: Role of TiO₂ substrate for high photocatalytic activity. *Appl Catal B: Environ* 2008; 79 117-121.
14. Kowalska E, Abe R, Ohtani B. Visible light-induced photocatalytic reaction of gold-modified-titanium(IV) oxide particles: action spectrum analysis. *Chem Commun*. 2009; 241.
15. Haruta M, Tsubota S, Kobayashi T, Kageyama H, Genet MJ, Delmon B. Low-temperature oxidation of CO over gold supported on TiO₂ α -Fe₂O₃, and Co₃O₄. *J Catal*. 1993; 144 175-192.
16. Kowalska E, Mahaney OOP, Abe R, Ohtani B. Visible-light-induced photocatalysis through surface plasmon excitation of gold on titania surfaces. *Phys Chem Chem Phys*. 2010; 12 2344-2355, and references therein.

- 421 17. Abe R, Hara K, Sayama K, Domen K, Arakawa H. Steady hydrogen evolution from
422 water on Eosin Y-fixed TiO₂ photocatalyst using a silane-coupling reagent under visible
423 light irradiation. *J Photochem Photobiol A: Chem.* 2000; 137 63-69.
- 424 18. Li Y, Guo M, Peng S, Lu G, Li S. Formation of multilayer-Eosin Y-sensitized TiO₂ via
425 Fe³⁺ coupling for efficient visible-light photocatalytic hydrogen evolution. *Int J Hydrogen*
426 *Energy.* 2009; 34 5629-5636.
- 427 19. Sreethawong T, Junbua C, Chavadej S. Photocatalytic H₂ production from water
428 splitting under visible light irradiation using Eosin Y-sensitized mesoporous-assembled
429 Pt/TiO₂ nanocrystal photocatalyst. *J Power Sources* 2009; 190 513-524.
- 430 20. Li Y, Xie C, Peng S, Lu G, Li S. Eosin Y-sensitized nitrogen-doped TiO₂ for efficient
431 visible light photocatalytic hydrogen evolution. *J Mol Catal A: Chem.* 2008; 282 117-123.
- 432 21. Nada AA, Hamed HA, Barakat MH, Mohamed NR, Veziroglu TN. Enhancement of
433 photocatalytic hydrogen production rate using photosensitized TiO₂/RuO₂-MV²⁺. *Int J*
434 *Hydrogen Energy.* 2008; 33 3264-3269.
- 435 22. O'Regan B, Grätzel M. A low-cost, high-efficiency solar cell based on dye-sensitized
436 colloidal TiO₂ films. *Nature.* 1991; 353 737-740.
- 437 23. Borgias BA, Cooper SR, Koh YB, Raymond KN. Synthetic, structural, and physical
438 studies of titanium complexes of catechol and 3,5-di-tert-butylcatechol. *Inorg Chem.*
439 1984; 23 1009-1016.
- 440 24. Liu Y, Dadap JI, Zimdars D, Eisenthal KB. Study of interfacial charge-transfer complex
441 on TiO₂ particles in aqueous suspension by second-harmonic generation. *J Phys Chem*
442 *B* 1999; 103 2480-2486.
- 443 25. Rodriguez R, Blesa MA, Regazzoni AE. Surface complexation at the
444 TiO₂(anatase)/aqueous solution interface: chemisorptions of catechol. *J Colloid*
445 *Interface Sci.* 1996; 177 122-131.
- 446 26. Moser J, Punchedewa S, Infelta PP, Grätzel M. Surface complexation of colloidal
447 semiconductors strongly enhances interfacial electron-transfer rates. *Langmuir.* 1991; 7
448 3012-3018.
- 449 27. Regazzoni AE, Mandelbaum P, Matsuyoshi M, Schiller S, Bilmes SA, Blesa MA.
450 Adsorption and photooxidation of salicylic acid on titanium dioxide: a surface
451 complexation description. *Langmuir.* 1998; 14 868-874.
- 452 28. Ikeda S, Abe C, Torimoto T, Ohtani B. Visible light-induced hydrogen evolution from
453 aqueous suspension of titanium(IV) oxide modified with binaphthol. *Electrochem.* 2002;
454 70(6) 442-445.
- 455 29. Ikeda S, Abe C, Torimoto T, Ohtani B. Photochemical hydrogen evolution from aqueous
456 triethanolamine solutions sensitized by binaphthol-modified titanium(IV) oxide under
457 visible-light irradiation. *J Photochem Photobiol A: Chem.* 2003;160 61-67, and
458 references therein.
- 459 30. Pope MT. Heteropoly and isopoly oxometalates. New York: Springer-Verlag; 1983.
- 460 31. Pope MT, Müller A. Chemistry of polyoxometalates. Actual variation on an old theme
461 with interdisciplinary references. *Angew Chem Int Ed Engl.* 1991; 30 34-48.
- 462 32. Pope MT, Müller A, editors; Polyoxometalates: from platonic solids to anti-retroviral
463 activity. Dordrecht, The Netherlands: Kluwer Academic Publishers; 1994.
- 464 33. Dubey N, Labhsetwar NK, Devotta S, Rayalu SR. Hydrogen evolution by water splitting
465 using novel composite zeolite-based photocatalyst. *Catal Today.* 2007;129 428-434.
- 466 34. Najafabadi AT, Taghipour F. Cobalt precursor role in the photocatalytic activity of the
467 zeolite-supported TiO₂-based photocatalysts under visible light: a promising tool toward
468 zeolite-based core-shell photocatalysis. *J Photochem Photobiol A: Chem.* 2012; 248 1-
469 7.
- 470 35. Fu N, Lu G. Graft of lacunary Wells-Dawson heteropoly blue on the surface of TiO₂ and
471 its photocatalytic activity under visible light. *Chem Commun.* 2009; 3591-3593.

36. Fu N, Wu Y, Jin Z, Lu G. Structural-dependent photoactivities of TiO₂ nanoribbon for visible-light-induced H₂ evolution: the roles of nanocavities and alternate structures. *Langmuir* 2010; 26(1) 447-455.
37. Fu N, Lu G. Photo-catalytic H₂ evolution over a series of Keggin-structure heteropolybule sensitized Pt/TiO₂ under visible light irradiation. *Appl Surf Sci.* 2009; 255 4378-4383.
38. Sivakumer R, Thomas J, Yoon M. Polyoxometalate-based molecular/nano composites: advances in environmental remediation by photocatalysis and biomimetic approaches to solar energy conversion. *J Photochem Photobiol C: Photochem Rev.* 2012; 13 277-298.
39. Kato CN, Hara K, Hatano A, Goto K, Kuribayashi T, Hayashi K, et al. A Dawson-type dirhenium(V)-oxido-bridged polyoxotungstate: X-ray crystal structure and hydrogen evolution from water vapor under visible light irradiation. *Eur J Inorg Chem.* 2008; 3134-3141.
40. Kato CN, Hara K, Kato M, Amano H, Sato K, Kataoka Y, et al. EDTA-reduction of water to molecular hydrogen catalyzed by visible-light-response TiO₂-based materials sensitized by Dawson- and Keggin-type rhenium(V)-containing polyoxotungstates. *Materials.* 2010; 3 897-917.
41. Contant R. Potassium octadecatungstodiphosphates(V) and related lacunary compounds. *Inorg Synth.* 1990; 27 104-110.
42. Lyon DK, Miller WK, Novet T, Domaille PJ, Evitt E, Johnson DC, Finke RG. Highly oxidation resistant inorganic-porphyrin analogue polyoxometalate oxidation catalysts. the synthesis and characterization of aqueous-soluble potassium salts of α_2 -P₂W₁₇O₆₁(Mⁿ⁺.OH₂)⁽ⁿ⁻¹⁰⁾ and organic solvent soluble tetra-n-butylammonium salts of α_2 -P₂W₁₇O₆₁(Mⁿ⁺.Br)⁽ⁿ⁻¹¹⁾ (M = Mn³⁺, Fe³⁺, Co²⁺, Ni²⁺, Cu²⁺). *J Am Chem Soc.* 1991; 113 7209-7221.
43. Weiner H, Aiken III JD, Finke RG. Polyoxometalate catalyst precursors. improved synthesis, H⁺-titration procedure, and evidence for ³¹P NMR as a highly sensitive support-site indication for the prototype polyoxoanion-organometallic-support system [(n-C₄H₉)₄N]₉P₂W₁₅Nb₃O₆₂. *Inorg Chem.* 1996; 35 7905-7913.
44. Sheldrick GM. A short history of SHELX. *Acta Crystallogr.* 2008; A64 112-122.
45. Spek AL. Structure validation in chemical crystallography. *Acta Crystallogr.* 2009; D65 148-155.
46. Nash T. The colorimetric estimation of formaldehyde by means of the hantzsch reaction. *Biochem J.* 1953; 55 416-421.
47. Ortéga F, Pope MT, Evans, Jr HT. Tungstoselenate heteropolyanions. 2. Synthesis and characterization of enneatungstoselenates(V), -(VI), and -(VII). *Inorg Chem.* 1997; 36 2166-2169.
48. Kato CN, Makino Y, Yamasaki M, Kataoka Y, Kitagawa Y, Okumura M. Synthesis and X-ray crystal structure of α -Keggin-type aluminum-substituted polyoxotungstate. In: Mastai Y editor. *Advances in crystallization processes.* Croatia: InTech; 2012.

APPENDIX

Bond lengths (Å) of **Me₂NH₂-1**: Re(1)(W(4))-O(8) 1.915(14); Re(1)(W(4))-O(14) 1.702(14); Re(1)(W(4))-O(19) 1.912(16); Re(1)(W(4))-O(20) 1.870(17); Re(1)(W(4))-O(26) 2.374(12); Re(1)(W(4))-O(57) 1.896(12); Re(2)(W(5))-O(9) 1.968(13); Re(2)(W(5))-O(15) 1.733(13); Re(2)(W(5))-O(20) 1.900(18); Re(2)(W(5))-O(21) 1.928(17); Re(2)(W(5))-O(27) 2.353(12); Re(2)(W(5))-O(58) 1.889(13); Re(3)(W(6))-O(10) 1.951(14); Re(3)(W(6))-O(16) 1.696(18); Re(3)(W(6))-O(21) 1.896(12); Re(3)(W(6))-O(22) 1.909(13); Re(3)(W(6))-O(27) 2.376(18); Re(3)(W(6))-O(59) 1.924(13); Re(4)(W(7))-O(11) 1.968(12); Re(4)(W(7))-O(17) 1.714(16); Re(4)(W(7))-O(22) 1.877(14); Re(4)(W(7))-O(23) 1.929(16); Re(4)(W(7))-O(28) 2.353(15);

525 Re(4)(W(7))-O(60) 1.893(13); Re(5)(W(8))-O(12) 1.951(13); Re(5)(W(8))-O(18) 1.689(14);
 526 Re(5)(W(8))-O(23) 1.891(17); Re(5)(W(8))-O(24) 1.906(15); Re(5)(W(8))-O(28) 2.360(13);
 527 Re(5)(W(8))-O(61) 1.881(12); Re(6)(W(9))-O(7) 1.905(14); Re(6)(W(9))-O(13) 1.691(17);
 528 Re(6)(W(9))-O(19) 1.899(13); Re(6)(W(9))-O(24) 1.866(13); Re(6)(W(9))-O(26) 2.379(16);
 529 Re(6)(W(9))-O(62) 1.924(14); Re(7)(W(10))-O(30) 1.708(16); Re(7)(W(10))-O(35) 1.916(16);
 530 Re(7)(W(10))-O(36) 1.863(16); Re(7)(W(10))-O(42) 1.943(12); Re(7)(W(10))-O(54)
 531 2.360(12); Re(7)(W(10))-O(57) 1.919(12); Re(8)(W(11))-O(31) 1.734(14); Re(8)(W(11))-
 532 O(36) 1.911(15); Re(8)(W(11))-O(37) 1.884(16); Re(8)(W(11))-O(43) 1.960(15);
 533 Re(8)(W(11))-O(55) 2.385(11); Re(8)(W(11))-O(58) 1.881(14); Re(9)(W(12))-O(32)
 534 1.689(18); Re(9)(W(12))-O(37) 1.941(12); Re(9)(W(12))-O(38) 1.879(12); Re(9)(W(12))-
 535 O(44) 1.968(14); Re(9)(W(12))-O(55) 2.345(16); Re(9)(W(12))-O(59) 1.861(13);
 536 Re(10)(W(13))-O(33) 1.694(15); Re(10)(W(13))-O(38) 1.892(13); Re(10)(W(13))-O(39)
 537 1.902(16); Re(10)(W(13))-O(45) 1.981(14); Re(10)(W(13))-O(56) 2.351(14); Re(10)(W(13))-
 538 O(60) 1.890(13); Re(11)(W(14))-O(34) 1.701(15); Re(11)(W(14))-O(39) 1.897(17);
 539 Re(11)(W(14))-O(40) 1.872(14); Re(11)(W(14))-O(46) 1.980(13); Re(11)(W(14))-O(56)
 540 2.374(13); Re(12)(W(15))-O(61) 1.891(13); Re(12)(W(15))-O(29) 1.679(19); Re(12)(W(15))-
 541 O(35) 1.907(12); Re(12)(W(15))-O(40) 1.899(13); Re(12)(W(15))-O(41) 1.958(13);
 542 Re(12)(W(15))-O(54) 2.384(16); Re(12)(W(15))-O(62) 1.867(13); W(1)-O(1) 1.690(11); W(1)-
 543 O(4) 1.921(15); W(1)-O(5) 1.910(15); W(1)-O(8) 1.912(16); W(1)-O(9) 1.870(14); W(1)-O(25)
 544 2.402(11); W(2)-O(2) 1.705(16); W(2)-O(5) 1.902(11); W(2)-O(6) 1.920(17); W(2)-O(10)
 545 1.880(15); W(2)-O(11) 1.882(12); W(2)-O(25) 2.364(15); W(3)-O(3) 1.692(14); W(3)-O(4)
 546 1.915(12); W(3)-O(6) 1.887(18); W(3)-O(7) 1.918(16); W(3)-O(12) 1.874(12); W(3)-O(25)
 547 2.386(13); W(16)-O(42) 1.892(15); W(16)-O(43) 1.874(17); W(16)-O(47) 1.730(14); W(16)-
 548 O(50) 1.908(15); W(16)-O(51) 1.932(15); W(16)-O(53) 2.415(12); W(17)-O(44) 1.865(15);
 549 W(17)-O(45) 1.865(13); W(17)-O(48) 1.680(14); W(17)-O(51) 1.898(14); W(17)-O(52)
 550 1.932(17); W(17)-O(53) 2.352(13); W(18)-O(41) 1.886(14); W(18)-O(46) 1.877(13); W(18)-
 551 O(49) 1.705(16); W(18)-O(50) 1.966(12); W(18)-O(52) 1.900(17); W(18)-O(53) 2.354(14);
 552 P(1)-O(25) 1.593(12); P(1)-O(26) 1.494(17); P(1)-O(27) 1.517(16); P(1)-O(28) 1.543(12);
 553 P(2)-O(53) 1.600(12); P(2)-O(54) 1.500(15); P(2)-O(55) 1.514(16); P(2)-O(56) 1.531(12).
 554

555 Bond angles (°) of **Me₂NH₂-1**: O(8)-Re(1)(W(4))-O(14) 97.6(6); O(8)-Re(1)(W(4))-O(19)
 556 89.9(7); O(8)-Re(1)(W(4))-O(20) 85.3(7); O(8)-Re(1)(W(4))-O(26) 81.4(5); O(8)-Re(1)(W(4))-
 557 O(57) 164.6(6); O(14)-Re(1)(W(4))-O(19) 99.4(7); O(14)-Re(1)(W(4))-O(20) 103.4(7); O(14)-
 558 Re(1)(W(4))-O(26) 172.2(7); O(14)-Re(1)(W(4))-O(57) 97.7(6); O(19)-Re(1)(W(4))-O(20)
 559 157.1(6); O(19)-Re(1)(W(4))-O(26) 72.9(6); O(19)-Re(1)(W(4))-O(57) 89.4(6); O(20)-
 560 Re(1)(W(4))-O(26) 84.3(6); O(20)-Re(1)(W(4))-O(57) 89.5(6); O(26)-Re(1)(W(4))-O(57)
 561 83.7(5); O(9)-Re(2)(W(5))-O(15) 97.4(6); O(9)-Re(2)(W(5))-O(20) 84.8(7); O(9)-Re(2)(W(5))-
 562 O(21) 88.1(6); O(9)-Re(2)(W(5))-O(27) 81.8(5); O(9)-Re(2)(W(5))-O(58) 163.3(6); O(15)-
 563 Re(2)(W(5))-O(20) 102.0(7); O(15)-Re(2)(W(5))-O(21) 99.5(7); O(15)-Re(2)(W(5))-O(27)
 564 173.0(8); O(15)-Re(2)(W(5))-O(58) 99.1(6); O(20)-Re(2)(W(5))-O(21) 158.1(6); O(20)-
 565 Re(2)(W(5))-O(27) 84.9(6); O(20)-Re(2)(W(5))-O(58) 89.5(7); O(21)-Re(2)(W(5))-O(27)
 566 73.5(6); O(21)-Re(2)(W(5))-O(58) 91.4(7); O(27)-Re(2)(W(5))-O(58) 82.1(5); O(10)-
 567 Re(3)(W(6))-O(16) 98.5(7); O(10)-Re(3)(W(6))-O(21) 88.0(6); O(10)-Re(3)(W(6))-O(22)
 568 86.8(6); O(10)-Re(3)(W(6))-O(27) 81.4(7); O(10)-Re(3)(W(6))-O(59) 163.6(8); O(16)-
 569 Re(3)(W(6))-O(21) 100.1(7); O(16)-Re(3)(W(6))-O(22) 102.0(7); O(16)-Re(3)(W(6))-O(27)
 570 173.7(5); O(16)-Re(3)(W(6))-O(59) 97.8(7); O(21)-Re(3)(W(6))-O(22) 157.7(8); O(21)-
 571 Re(3)(W(6))-O(27) 73.5(6); O(21)-Re(3)(W(6))-O(59) 90.8(6); O(22)-Re(3)(W(6))-O(27)
 572 84.3(7); O(22)-Re(3)(W(6))-O(59) 88.1(6); O(27)-Re(3)(W(6))-O(59) 82.6(6); O(11)-
 573 Re(4)(W(7))-O(17) 96.9(6); O(11)-Re(4)(W(7))-O(22) 86.0(6); O(11)-Re(4)(W(7))-O(23)
 574 87.8(6); O(11)-Re(4)(W(7))-O(28) 81.7(6); O(11)-Re(4)(W(7))-O(60) 163.4(6); O(17)-
 575 Re(4)(W(7))-O(22) 102.7(8); O(17)-Re(4)(W(7))-O(23) 99.3(7); O(17)-Re(4)(W(7))-O(28)
 576 172.2(6); O(17)-Re(4)(W(7))-O(60) 99.6(6); O(22)-Re(4)(W(7))-O(23) 157.7(7); O(22)-
 577 Re(4)(W(7))-O(28) 84.9(6); O(22)-Re(4)(W(7))-O(60) 89.1(6); O(23)-Re(4)(W(7))-O(28)

578 73.0(6); O(23)-Re(4)(W(7))-O(60) 90.8(6); O(28)-Re(4)(W(7))-O(60) 82.1(6); O(12)-
579 Re(5)(W(8))-O(18) 97.7(6); O(12)-Re(5)(W(8))-O(23) 89.1(7); O(12)-Re(5)(W(8))-O(24)
580 84.5(6); O(12)-Re(5)(W(8))-O(28) 81.5(5); O(12)-Re(5)(W(8))-O(61) 162.6(5); O(18)-
581 Re(5)(W(8))-O(23) 99.0(7); O(18)-Re(5)(W(8))-O(24) 102.5(7); O(18)-Re(5)(W(8))-O(28)
582 172.4(7); O(18)-Re(5)(W(8))-O(61) 99.3(6); O(23)-Re(5)(W(8))-O(24) 158.3(6); O(23)-
583 Re(5)(W(8))-O(28) 73.5(6); O(23)-Re(5)(W(8))-O(61) 91.9(7); O(24)-Re(5)(W(8))-O(28)
584 85.1(6); O(24)-Re(5)(W(8))-O(61) 88.3(6); O(28)-Re(5)(W(8))-O(61) 82.1(5); O(7)-
585 Re(6)(W(9))-O(13) 97.4(7); O(7)-Re(6)(W(9))-O(19) 89.2(6); O(7)-Re(6)(W(9))-O(24)
586 87.0(6); O(7)-Re(6)(W(9))-O(26) 81.7(6); O(7)-Re(6)(W(9))-O(62) 163.7(7); O(13)-
587 Re(6)(W(9))-O(19) 100.8(7); O(13)-Re(6)(W(9))-O(24) 101.6(7); O(13)-Re(6)(W(9))-O(26)
588 173.7(5); O(13)-Re(6)(W(9))-O(62) 98.9(7); O(19)-Re(6)(W(9))-O(24) 157.6(8); O(19)-
589 Re(6)(W(9))-O(26) 73.0(6); O(19)-Re(6)(W(9))-O(62) 88.2(6); O(24)-Re(6)(W(9))-O(26)
590 84.6(6); O(24)-Re(6)(W(9))-O(62) 89.2(6); O(26)-Re(6)(W(9))-O(62) 82.1(6); O(30)-
591 Re(7)(W(10))-O(35) 99.4(8); O(30)-Re(7)(W(10))-O(36) 103.2(7); O(30)-Re(7)(W(10))-O(42)
592 96.7(6); O(30)-Re(7)(W(10))-O(54) 172.0(7); O(30)-Re(7)(W(10))-O(57) 99.0(6); O(35)-
593 Re(7)(W(10))-O(36) 157.2(6); O(35)-Re(7)(W(10))-O(42) 87.2(6); O(35)-Re(7)(W(10))-O(54)
594 72.8(6); O(35)-Re(7)(W(10))-O(57) 88.4(6); O(36)-Re(7)(W(10))-O(42) 87.4(6); O(36)-
595 Re(7)(W(10))-O(54) 84.5(5); O(36)-Re(7)(W(10))-O(57) 90.8(6); O(42)-Re(7)(W(10))-O(54)
596 81.2(5); O(42)-Re(7)(W(10))-O(57) 164.2(6); O(54)-Re(7)(W(10))-O(57) 82.9(5); O(31)-
597 Re(8)(W(11))-O(36) 102.7(7); O(31)-Re(8)(W(11))-O(37) 99.2(7); O(31)-Re(8)(W(11))-O(43)
598 98.5(7); O(31)-Re(8)(W(11))-O(55) 172.6(8); O(31)-Re(8)(W(11))-O(58) 98.3(6); O(36)-
599 Re(8)(W(11))-O(37) 158.1(5); O(36)-Re(8)(W(11))-O(43) 85.7(7); O(36)-Re(8)(W(11))-O(55)
600 84.8(5); O(36)-Re(8)(W(11))-O(58) 86.6(7); O(37)-Re(8)(W(11))-O(43) 90.8(7); O(37)-
601 Re(8)(W(11))-O(55) 73.4(6); O(37)-Re(8)(W(11))-O(58) 90.6(7); O(43)-Re(8)(W(11))-O(55)
602 82.3(5); O(43)-Re(8)(W(11))-O(58) 162.8(6); O(55)-Re(8)(W(11))-O(58) 81.7(5); O(32)-
603 Re(9)(W(12))-O(37) 100.3(7); O(32)-Re(9)(W(12))-O(38) 101.6(7); O(32)-Re(9)(W(12))-
604 O(44) 96.9(7); O(32)-Re(9)(W(12))-O(55) 173.4(5); O(32)-Re(9)(W(12))-O(59) 98.5(7);
605 O(37)-Re(9)(W(12))-O(38) 157.8(7); O(37)-Re(9)(W(12))-O(44) 88.8(6); O(37)-Re(9)(W(12))-
606 O(55) 73.4(6); O(37)-Re(9)(W(12))-O(59) 88.9(6); O(38)-Re(9)(W(12))-O(44) 85.4(6); O(38)-
607 Re(9)(W(12))-O(55) 84.6(6); O(38)-Re(9)(W(12))-O(59) 91.1(6); O(44)-Re(9)(W(12))-O(55)
608 81.2(6); O(44)-Re(9)(W(12))-O(59) 164.6(7); O(55)-Re(9)(W(12))-O(59) 83.6(6); O(33)-
609 Re(10)(W(13))-O(38) 101.9(7); O(33)-Re(10)(W(13))-O(39) 100.0(7); O(33)-Re(10)(W(13))-
610 O(45) 96.1(6); O(33)-Re(10)(W(13))-O(56) 172.5(6); O(33)-Re(10)(W(13))-O(60) 100.7(7);
611 O(38)-Re(10)(W(13))-O(39) 157.6(7); O(38)-Re(10)(W(13))-O(45) 84.7(6); O(38)-
612 Re(10)(W(13))-O(56) 84.7(6); O(38)-Re(10)(W(13))-O(60) 88.5(6); O(39)-Re(10)(W(13))-
613 O(45) 88.6(6); O(39)-Re(10)(W(13))-O(56) 73.1(6); O(39)-Re(10)(W(13))-O(60) 91.8(6);
614 O(45)-Re(10)(W(13))-O(56) 80.9(5); O(45)-Re(10)(W(13))-O(60) 162.8(6); O(56)-
615 Re(10)(W(13))-O(60) 82.7(6); O(34)-Re(11)(W(14))-O(39) 100.0(7); O(34)-Re(11)(W(14))-
616 O(40) 102.2(8); O(34)-Re(11)(W(14))-O(46) 96.5(7); O(34)-Re(11)(W(14))-O(56) 172.5(7);
617 O(34)-Re(11)(W(14))-O(61) 99.5(6); O(39)-Re(11)(W(14))-O(40) 157.3(6); O(39)-
618 Re(11)(W(14))-O(46) 87.3(7); O(39)-Re(11)(W(14))-O(56) 72.7(5); O(39)-Re(11)(W(14))-
619 O(61) 91.2(7); O(40)-Re(11)(W(14))-O(46) 85.6(6); O(40)-Re(11)(W(14))-O(56) 85.0(6);
620 O(40)-Re(11)(W(14))-O(61) 89.8(6); O(46)-Re(11)(W(14))-O(56) 82.1(5); O(46)-
621 Re(11)(W(14))-O(61) 163.9(6); O(56)-Re(11)(W(14))-O(61) 82.2(5); O(29)-Re(12)(W(15))-
622 O(35) 100.3(7); O(29)-Re(12)(W(15))-O(40) 101.8(7); O(29)-Re(12)(W(15))-O(41) 96.3(7);
623 O(29)-Re(12)(W(15))-O(54) 172.4(6); O(29)-Re(12)(W(15))-O(62) 99.3(7); O(35)-
624 Re(12)(W(15))-O(40) 157.3(7); O(35)-Re(12)(W(15))-O(41) 88.0(5); O(35)-Re(12)(W(15))-
625 O(54) 72.4(6); O(35)-Re(12)(W(15))-O(62) 91.2(6); O(40)-Re(12)(W(15))-O(41) 84.6(6);
626 O(40)-Re(12)(W(15))-O(54) 85.3(6); O(40)-Re(12)(W(15))-O(62) 90.1(6); O(41)-
627 Re(12)(W(15))-O(54) 81.4(6); O(41)-Re(12)(W(15))-O(62) 164.2(8); O(54)-Re(12)(W(15))-
628 O(62) 83.4(6); O(1)-W(1)-O(4) 102.0(6); O(1)-W(1)-O(5) 101.9(7); O(1)-W(1)-O(8) 102.5(7);
629 O(1)-W(1)-O(9) 102.1(6); O(1)-W(1)-O(25) 171.7(6); O(4)-W(1)-O(5) 88.7(7); O(4)-W(1)-O(8)
630 87.0(7); O(4)-W(1)-O(9) 155.9(6); O(4)-W(1)-O(25) 72.9(5); O(5)-W(1)-O(8) 155.5(5); O(5)-

631 W(1)-O(9) 88.2(7); O(5)-W(1)-O(25) 71.8(5); O(8)-W(1)-O(9) 86.1(7); O(8)-W(1)-O(25)
632 83.9(5); O(9)-W(1)-O(25) 83.5(5); O(2)-W(2)-O(5) 102.4(6); O(2)-W(2)-O(6) 101.5(7); O(2)-
633 W(2)-O(10) 103.6(8); O(2)-W(2)-O(11) 101.8(7); O(2)-W(2)-O(25) 171.7(6); O(5)-W(2)-O(6)
634 87.7(6); O(5)-W(2)-O(10) 87.2(6); O(5)-W(2)-O(11) 155.8(7); O(5)-W(2)-O(25) 72.9(6); O(6)-
635 W(2)-O(10) 154.9(7); O(6)-W(2)-O(11) 87.1(6); O(6)-W(2)-O(25) 71.8(6); O(10)-W(2)-O(11)
636 87.6(6); O(10)-W(2)-O(25) 83.3(7); O(11)-W(2)-O(25) 83.0(6); O(3)-W(3)-O(4) 103.2(6);
637 O(3)-W(3)-O(6) 101.7(7); O(3)-W(3)-O(7) 102.2(7); O(3)-W(3)-O(12) 101.3(6); O(3)-W(3)-
638 O(25) 172.4(7); O(4)-W(3)-O(6) 89.2(7); O(4)-W(3)-O(7) 87.4(6); O(4)-W(3)-O(12) 155.4(6);
639 O(4)-W(3)-O(25) 73.4(5); O(6)-W(3)-O(7) 156.0(6); O(6)-W(3)-O(12) 88.0(7); O(6)-W(3)-
640 O(25) 71.7(6); O(7)-W(3)-O(12) 85.4(6); O(7)-W(3)-O(25) 84.5(6); O(12)-W(3)-O(25) 82.6(5);
641 O(42)-W(16)-O(43) 87.8(7); O(42)-W(16)-O(47) 102.4(7); O(42)-W(16)-O(50) 87.8(6); O(42)-
642 W(16)-O(51) 155.2(6); O(42)-W(16)-O(53) 82.9(5); O(43)-W(16)-O(47) 103.3(7); O(43)-
643 W(16)-O(50) 157.1(6); O(43)-W(16)-O(51) 89.2(7); O(43)-W(16)-O(53) 84.0(6); O(47)-
644 W(16)-O(50) 99.6(7); O(47)-W(16)-O(51) 102.2(7); O(47)-W(16)-O(53) 171.0(5); O(50)-
645 W(16)-O(51) 85.4(7); O(50)-W(16)-O(53) 73.1(6); O(51)-W(16)-O(53) 72.3(5); O(44)-W(17)-
646 O(45) 86.8(6); O(44)-W(17)-O(48) 101.3(7); O(44)-W(17)-O(51) 91.4(6); O(44)-W(17)-O(52)
647 157.7(6); O(44)-W(17)-O(53) 85.4(6); O(45)-W(17)-O(48) 102.4(6); O(45)-W(17)-O(51)
648 157.3(7); O(45)-W(17)-O(52) 87.9(7); O(45)-W(17)-O(53) 82.9(6); O(48)-W(17)-O(51)
649 100.1(6); O(48)-W(17)-O(52) 100.9(7); O(48)-W(17)-O(53) 171.5(7); O(51)-W(17)-O(52)
650 85.3(7); O(51)-W(17)-O(53) 74.4(5); O(52)-W(17)-O(53) 72.4(6); O(41)-W(18)-O(46) 87.6(6);
651 O(41)-W(18)-O(49) 101.8(8); O(41)-W(18)-O(50) 89.3(6); O(41)-W(18)-O(52) 157.7(7);
652 O(41)-W(18)-O(53) 84.8(6); O(46)-W(18)-O(49) 102.1(7); O(46)-W(18)-O(50) 158.9(7);
653 O(46)-W(18)-O(52) 89.4(7); O(46)-W(18)-O(53) 85.3(6); O(49)-W(18)-O(50) 98.9(7); O(49)-
654 W(18)-O(52) 100.5(7); O(49)-W(18)-O(53) 170.2(6); O(50)-W(18)-O(52) 85.7(6); O(50)-
655 W(18)-O(53) 73.6(6); O(52)-W(18)-O(53) 72.9(6); O(25)-P(1)-O(26) 107.4(8); O(25)-P(1)-
656 O(27) 106.8(8); O(25)-P(1)-O(28) 106.4(7); O(26)-P(1)-O(27) 112.6(8); O(26)-P(1)-O(28)
657 112.2(8); O(27)-P(1)-O(28) 111.0(8); O(53)-P(2)-O(54) 107.0(8); O(53)-P(2)-O(55) 106.4(7);
658 O(53)-P(2)-O(56) 106.3(6); O(54)-P(2)-O(55) 112.9(7); O(54)-P(2)-O(56) 113.0(8); O(55)-
659 P(2)-O(56) 110.8(8); W(1)-O(4)-W(3) 123.7(7); W(1)-O(5)-W(2) 124.9(7); W(2)-O(6)-W(3)
660 125.5(7); Re(6)(W(9))-O(7)-W(3) 150.1(8); Re(1)(W(4))-O(8)-W(1) 151.3(9); Re(2)(W(5))-
661 O(9)-W(1) 150.7(10); Re(3)(W(6))-O(10)-W(2) 150.0(9); Re(4)(W(7))-O(11)-W(2) 150.4(7);
662 Re(5)(W(8))-O(12)-W(3) 153.0(8); Re(1)(W(4))-O(19)-Re(6)(W(9)) 124.0(9); Re(1)(W(4))-
663 O(20)-Re(2)(W(5)) 152.9(8); Re(2)(W(5))-O(21)-Re(3)(W(6)) 122.4(8); Re(3)(W(6))-O(22)-
664 Re(4)(W(7)) 151.7(9); Re(4)(W(7))-O(23)-Re(5)(W(8)) 122.6(7); Re(5)(W(8))-O(24)-
665 Re(6)(W(9)) 151.7(9); W(1)-O(25)-W(2) 90.3(5); W(1)-O(25)-W(3) 89.9(4); W(1)-O(25)-P(1)
666 123.8(6); W(2)-O(25)-W(3) 90.9(4); W(2)-O(25)-P(1) 126.4(8); W(3)-O(25)-P(1) 124.7(8);
667 Re(1)(W(4))-O(26)-Re(6)(W(9)) 90.1(6); Re(1)(W(4))-O(26)-P(1) 128.6(8); Re(6)(W(9))-
668 O(26)-P(1) 128.6(7); Re(2)(W(5))-O(27)-Re(3)(W(6)) 90.3(6); Re(2)(W(5))-O(27)-P(1)
669 127.8(8); Re(3)(W(6))-O(27)-P(1) 128.3(8); Re(4)(W(7))-O(28)-Re(5)(W(8)) 90.6(4);
670 Re(4)(W(7))-O(28)-P(1) 128.2(9); Re(5)(W(8))-O(28)-P(1) 127.2(8); Re(7)(W(10))-O(35)-
671 Re(12)(W(15)) 123.9(9); Re(7)(W(10))-O(36)-Re(8)(W(11)) 151.8(6); Re(8)(W(11))-O(37)-
672 Re(9)(W(12)) 122.7(8); Re(9)(W(12))-O(38)-Re(10)(W(13)) 152.9(9); Re(10)(W(13))-O(39)-
673 Re(11)(W(14)) 123.6(7); Re(11)(W(14))-O(40)-Re(12)(W(15)) 153.3(8); Re(12)(W(15))-
674 O(41)-W(18) 150.1(9); Re(7)(W(10))-O(42)-W(16) 149.4(10); Re(8)(W(11))-O(43)-W(16)
675 150.4(10); Re(9)(W(12))-O(44)-W(17) 150.1(8); Re(10)(W(13))-O(45)-W(17) 151.1(7);
676 Re(11)(W(14))-O(46)-W(18) 148.4(7); W(16)-O(50)-W(18) 122.5(8); W(16)-O(51)-W(17)
677 123.3(7); W(17)-O(52)-W(18) 123.2(7); W(16)-O(53)-W(17) 90.0(4); W(16)-O(53)-W(18)
678 90.8(5); W(16)-O(53)-P(2) 124.1(6); W(17)-O(53)-W(18) 91.5(4); W(17)-O(53)-P(2) 125.3(9);
679 W(18)-O(53)-P(2) 124.9(8); Re(7)(W(10))-O(54)-Re(12)(W(15)) 90.6(6); Re(7)(W(10))-
680 O(54)-P(2) 129.0(7); Re(12)(W(15))-O(54)-P(2) 127.8(7); Re(8)(W(11))-O(55)-Re(9)(W(12))
681 90.4(5); Re(8)(W(11))-O(55)-P(2) 127.2(8); Re(9)(W(12))-O(55)-P(2) 130.2(7);
682 Re(10)(W(13))-O(56)-Re(11)(W(14)) 90.3(4); Re(10)(W(13))-O(56)-P(2) 128.6(8);
683 Re(11)(W(14))-O(56)-P(2) 127.8(9); Re(1)(W(4))-O(57)-Re(7)(W(10)) 160.2(10);

684 Re(2)(W(5))-O(58)-Re(8)(W(11)) 165.3(11); Re(3)(W(6))-O(59)-Re(9)(W(12)) 162.0(8);
685 Re(4)(W(7))-O(60)-Re(10)(W(13)) 163.4(8); Re(5)(W(8))-O(61)-Re(11)(W(14)) 163.7(9);
686 Re(6)(W(9))-O(62)-Re(12)(W(15)) 162.0(9).
687
688
689